

Formaldehyde Emission Summary – E0 MDF

REPORT NO. 10MDF-E0

Company Name:
The Laminex Group

Report Date:
8/12/2010

Product Standard:
AS/NZS 1859.2:2004

Test Method:
AS/NZS 4266.16:2004

AS/NZS Limits:
≤0.5 mg/L

		E0 MR MDF					
Thickness (mm)		9	12	16	18	25	32
Result (mg/L)		0.47	0.45	0.40	0.44	0.39	0.43

		E0 STD MDF							
Thickness (mm)		3	6	9	12	16	18	25	32
Result (mg/L)		0.22	0.13	0.24	0.28	0.17	0.24	0.20	0.20

Testing completed and traceable to the following NATA accredited laboratories

The Laminex Group Technology Centre. NATA accreditation number 15305
AWPA Test Centre Association Inc. NATA accreditation number 14292

Emission values stated are specific for the sample tested.

Authority:


Cameron Dellar
R&D Manager